


The Degaflex Roofing System is a fast curing, high performance methyl methacrylate (MMA) waterproofing system for use in flat roofing and roofing repairs. The system has been tested by BRE Global Ltd and has achieved an excellent Fire Rating to BS 476 Part 3 EXT.F.AB.

Degaflex encapsulates fibreglass chop strand matting to produce a flexible, yet very strong, water resistant and fire retardant membrane. Each layer of the system cures within 30 minutes allowing the complete system to be fully cured in less than 2 hours.

Its ability to cure at temperatures as low as -5°C allows for quick repairs throughout the year. Slip resistance may also be included for walkways and access areas.

Degaflex may be Smooth or Textured and is available in many colours.



**Rapid installation – fully cured within 2 hours**



**Exceptional bond to a wide range of substrates**



**Seamless and impermeable surface without pinholes or air bubbles**



**Exceptional resistant to chemical and physical attack**



**Tailored slip resistant finishes**



**Fire Resistant to BS 476 Part 3**



**BS EN ISO 9001 : 2015 Certificate 20/Q064  
Quality Management Systems**

EN 1504-2:2004 Certificate Number 0086 CPR 717136.	
Abrasion resistance	Weight loss < 3000 mg
Permeability to CO <sup>2</sup>	SD > 50 m
Water vapour permeability	Class III
Capillary absorption and permeability to water	W < 0.1 kg / (m <sup>2</sup> x h <sup>0.5</sup> )
Resistance to severe chemical attack	Reduction in hardness < 50%
Impact resistance	Class I
Adhesion strength by pull of test	≥ 2.0 N/mm <sup>2</sup>
Reaction to fire	BS 476 Part 3:- EXT.F.AB